


AP-112

Aprestine®

STANDARD

Plaster suitable for covering and smoothing walls with small flaws.
Slow setting.



* information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions).

INDOOR



USE

Gypsum, plaster, cement, non-elastic synthetic paint.
Surfaces must be healthy, dry, cohesive, absorbent, well adhered, clean and free of dust.

FEATURES

- Slow drying.
- Easy to apply, smooth and sand.
- Non-repellent
- A thin coat can be applied.
- Storage: 12 months inside its original packing and kept free from damp and humidity.

IDEAL FOR

- Covering of small fissures and micro-fissures.
- Smoothing of walls with flaws (scratches, lines, bumps ...).



COATED

BY ALL KINDS OF CONVENTIONAL NON- RESILIENT
PAINTS AFTER COMPLETE DRYING

CLASSIFICATION ACCORDING TO
UNE 48313: 2008 EX

G3E5S2V3W2A0C0



15Kg Pallet of 66 sacks
x 15 Kgs.

5Kg Pallet of 35 cases
of 4 x 5 Kgs

1Kg Pallet of 36 cases of
20 x 1 Kg.



PREPARATION

0.38 to 0.43 litres of water per Kg. of
plaster



PERFORMANCE

1.65-1.80 Kg/m²/mm



6.0-7.0



MAXIMUM THICKNESS PER COAT

1 mm



ADHESION

>7kg/cm² on cement and paint



FIRE RESISTANCE CLASSIFICATION

A1



USEFUL LIFE

7 - 8 Hrs. approx.



DRYING TIME

Concrete and paint: 4 - 6 hrs.
Gypsum: 9 - 10 hrs



MAXIMUM GRADING

300 microns