

AP-200

Aprestine®

## THIN EXTERIORS

Fine plaster designed for covering and smoothing façades and walls.



EXTERIOR



## COVERING

FOR ALL TYPES OF CONVENTIONAL PAINT  
AFTER COMPLETE DRYING (1)

CLASSIFICATION (EN 16566)

G3S2V2W2A0C0R0

## SURFACES

Cement, concrete, laminated cement slabs, brick partitions, stone, non-elastic paint residues.  
Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

## CHARACTERISTICS

- Easy to apply.
- White.
- Applicable in thin and thick layers.
- Easy to sand.
- Thin product.
- Slow setting.
- Waterproof product.


## IDEAL FOR

- Repairing cracks and micro-fissures.
- Covering immobile and non-structural cracks.
- Smoothing and plastering exterior walls.

## ON-SITE APPLICATION

## SURFACE PREPARATION

The surface must be sound, clean and free of any trace of saltpetre, fungi, microorganisms, grease, release oils and, in general, any type of material that could make it difficult for the product to adhere to the surface.



AP-200

Aprestine®

## THIN EXTERIORS

### ON-SITE APPLICATION

#### CLEANING

When the supports present traces of fungi, algae or other types of microorganisms, we will proceed with the curative treatment, first of all, with a quick mold cleaner. This will be applied to the surface to be treated and after 5 -10 minutes of action, the support will be cleaned with the help of a pressurized water machine or with a hard bristle brush. Next, and once the support is completely dry, a broad-spectrum biocide cleaner will be applied until the support is completely impregnated. This treatment is called preventive, it is very effective and serves to prevent the future appearance of microorganisms.

If there are saltpetre stains on the surface to be treated, carry out an initial cleaning process with our **RX-523 CLEAN SAL**, applying the material and then scraping it with a hard bristle brush. After mechanically cleaning the surface, it will need to be rinsed with plenty of clean water in order to neutralise any **CLEAN SAL** residue that may remain on the surface.

Any grease or oil must be completely eliminated to allow the product to adhere correctly to the surface. Therefore, we recommend using **RX-527 CLEAN OIL** for correct and total elimination of these substances.

Powdery surfaces must be consolidated with a fixative (**FIJAPREN** line), since dust prevents adhesion between materials. Similarly, old surfaces made up of perished plaster or poorly adhered parts must be cleaned up: **restoring perished surfaces without prior restoration is totally inadvisable**. If there are holes in the surface, these should be scraped down and removed until a consistent surface is created, then a fixative (**FIJAPREN** line) should be applied to remove traces of dust. This consistent surface will usually be made of brick, cement, functional plaster or any other material, as long as it can support the weight and tension of the layers subsequently applied, without breaking up or having its structure altered.

If cracks are present these must be repaired, i.e. opened up and their interiors fixed using a fixative (**FIJAPREN** line), left to dry for at least 4 hours and then filled to the required level. If the cracks are structural, it is required to create perimeter joints in the façade, in order to absorb and/or derive movement.

#### DIRECTIONS FOR USE

Mix with clean water at a ratio of 35 - 40 % (350 ml - 400 ml water for each kg of plaster). Mixing should be carried out manually or mechanically using an electric mixer. Leave the paste to stand for a few minutes and then apply.

For cavity filling, we recommend using a medium sized spatula that allows for good pressure inside the cavity. Where possible, ensure that the width of the spatula is slightly greater than the size of the cavity.

All those areas of a façade that are subject to stress (such as expansion joints or boundary joints of different materials), must be reinforced with fibreglass mesh that is resistant to the alkalinity of the cement in order to avoid cracking of the plaster. The mesh will remain inside (plaster-mesh-plaster) and will extend approximately 25 centimetres each side of these joints subject to stress. We recommend the application of our **RG-116** fibreglass mesh.

When the material is dry, sand it and, if there are no imperfections, apply a fixative and then paint.

# AP-200

## EXTERIOR POWDERED PRODUCT



### Aprestine®

## THIN EXTERIORS

### TECHNICAL CHARACTERISTICS

|                             |                   |
|-----------------------------|-------------------|
| Useful life                 | 2 H 30' - 3 H 30' |
| Reaction to fire            | A1                |
| Maximum granulometry        | 300 µm            |
| Maximum thickness per layer | 10 mm             |
| pH                          | 12 - 13           |
| Shore C hardness            | 75                |

|   |            |
|---|------------|
| Drying time in 1 mm layer on concrete surface (*)               | 3 - 4 h    |
| Mean value of the apparent dry density (S/UNE-EN 1015-10)       | 1325 kg/m³ |
| Coefficient of water vapour permeability (µ) (S/UNE-EN 1015-19) | 0,20       |
| Thermal conductivity (W/mK) (S/UNE-EN 1745:2002)                | 0.58 W/mK  |
| Tool cleaning   | With water |

(\*) Depends on the environmental conditions, the nature of the surface and the thickness of application.

| DENSITY        |               |
|----------------|---------------|
| POWDER (gr/ml) | PASTE (gr/ml) |
| 0.87 ± 0.07    | 1.49 ± 0.07   |

| PERFORMANCE  |             |
|--|-------------|
| kilograms of powder applied per m² in 1 mm thickness | 1.15 - 1.20 |

| ADHERENCES<br>(on cement/paint substrates - 2 mm layer) |            |
|---|------------|
| TEST  | RESULT     |
| Initial adhesion (28d)                                  | > 7 Kg/cm² |
| Ageing with heat  | > 5 Kg/cm² |
| Immersion treatment                                     | > 9 Kg/cm² |
| Climate Cycles  | > 5 Kg/cm² |

| RESISTANCE TO BENDING AND COMPRESSION (S/UNE-EN 1015-11) |             |
|--|-------------|
| MEAN BENDING STRENGTH                                    | ≥ 3.0 N/mm² |
| MEDIUM COMPRESSIVE STRENGTH                              | ≥ 8.0 N/mm² |
| CLASSIFICATION   | CS IV       |

| SUBSCRIPTION (N/mm² AND FORM OF BREAKING (FP)<br>A,B Ó C SEGÚN UNE-EN 1015-12 |                           |
|---|---------------------------|
| THICKNESS   | 10 mm layer               |
| SURFACES  | Concrete                  |
| AVERAGE TENSILE STRENGTH  | Superior a 0.5 N/mm²      |
| FP  | B (average CF-A failures) |

| WATER ABSORPTION BY CAPILLARITY (CATEGORIES)<br>ACCORDING TO UNE-EN 1015-18 |    |
|---|----|
| CLASSIFICATION  | W2 |

| WATER PERMEABILITY AFTER CAPILLARY WATER ABSORPTION TEST<br>ACCORDING TO UNE-EN 1015-21 (ml/cm² 48H) |                 |                  |
|--|-----------------|------------------|
| THICKNESS  | MASONRY SURFACE | CONCRETE SURFACE |
| 1 cm   | 1.3             | 1.3              |
| 2 cm   | 1.3             | 1.3              |

# AP-200

Aprestine®

## THIN EXTERIORS

### INFORMATION OF INTEREST

The Aprestine range manufacturing process is controlled in batches, which allows traceability of any incident. The quality system used includes each article's design and production controls, both in terms of the raw materials used, guaranteeing uniform manufacturing, and the final item obtained. The use of ecotechnologies in our facilities' manufacturing processes allows for efficient work, without damaging the environment that surrounds us.

- Non-flammable product. Irritating.
- Avoid bringing the product into contact with skin and eyes.
- Smoking, eating and drinking must be prohibited in the application area.
- Comply with workplace health and safety legislation.
- Keep the product in a dry place, in original containers that are kept properly closed.
- Store the containers between 5°C and 35°C.
- Recommended storage time: 12 months from the date of manufacture, in its original packaging and protected from moisture.

For further information on protective measures and first aid, please refer to the product's Safety Data Sheet.

### COMMENTS

(1) **APRESTINE AP-200** can be coated with any conventional paint (provided it is breathable and resistant to cement alkalis). If we want to apply a coloured plastic paint on the **AP-200** and to avoid it becoming discoloured, we must first apply a coat of our product **RX-517 CONCRETE MICROPRIMER** and then apply the paint normally.

- For appropriate use and correct application of the product, it is essential to first read the technical data sheet.
- The data provided in this data sheet are for guidance only and should not be considered binding. The data has been obtained in normal laboratory conditions and on standardised surfaces, and can vary depending on the conditions in which they are applied (absorption of the surface, applied thickness, temperature, environmental humidity, etc.). The intervals displayed have been shaped by measurement history. Slight deviations from the ranges presented in this technical sheet, whether higher or lower, will be accepted according to internal technical criteria and will not result in a loss of quality or affect the performance of the final product, due, among other factors, to variations in measurement conditions and the uncertainty associated with the instruments used.
- The working conditions of the users are out of our control.
- The product must not be used for purposes other than those specified. We recommend strictly following the recommendations for use.
- Do not exceed the maximum recommended application thickness.
- It is essential that the status of the surfaces be assessed prior to each application.
- Use the product within its useful lifetime. Beyond this time, unfavourable properties may arise.
- Do not apply on wet surfaces.
- Do not apply on non-absorbent or extremely crystalline surfaces.
- Application temperature: from 5°C to 35°C.
- Maximum relative humidity: 85%.
- Do not mix with any material, as the product will not retain its technical characteristics.
- Do not re-mix when the product has started to set.

AP-200

Aprestine®

## THIN EXTERIORS

## COMMENTS

- The technical department of **ESTABLECIMIENTOS BAIXENS** states that the designs of recently launched new products are considered to be in an experimental phase until an annual history can be constituted. From then on, the newly designed product is considered to be fully consolidated in the market. In the meantime, **BAIXENS** reserves the right to adapt its variable specifications or working ranges according to technical criteria. The data subject to modification will be identified with an asterisk for easy identification and may be recently created products and / or experimental phase products or improvements in our various ranges due to market needs and / or requirements.
- We place at your disposal a technical-commercial team that will advise you regarding any doubt or query.

## PACKAGING

| FORMAT   | 15 Kg    | 5 Kg     | 1 Kg     |
|----------|----------|----------|----------|
| UNIT/BOX | –        | 4        | 20       |
| PALLETS  | 72 SACKS | 35 BOXES | 36 BOXES |



|               |                |
|---------------|----------------|
| Internal code | AP200NF1449A20 |
|---------------|----------------|


**BAIXENS**  
 baixens.com

*Testing the difference*

**BAIXENS ESPAÑA**  
 POL. IND. MONCARRA, S/N  
 46230 ALGINET (VALENCIA)  
 T.: 961.750.834  
 F.: 961.752.471

**BAIXENS FRANCE**  
 14, RUE DU PONT NEUF  
 75001 PARIS (FRANCE)  
 T.: 0.800.90.14.37  
 F.: 0.800.90.20.52

**BAIXENS ITALIA / BULOVA**  
 VIA PIETRO NENNI, 36  
 46019 CICOGNARA - MANTOVA (ITALY)  
 T.: 0375/88181/790016 F.: 0375/88831  
 www.bulova-pennelli.com

**BAIXENS PORTUGAL / ARGATINTAS**  
 AVENIDA PORTAS DO MINHO, Nº 711  
 4760 - 706 RIBEIRÃO,  
 V.N. FAMALICÃO  
 T.: 252 910 030  
 www.argatintas.pt