

B-39

Brico

PORTLAND CEMENT MORTAR

Product suitable for all types of applications in masonry plastering.



EXTERIOR



CLASSIFICATION ACCORDING TO STANDARD EN 16566

G3S3V3W2A0C0R0

SURFACES

Cement, stone, brick, concrete, concrete structures, cement mortars and any absorbent building surface.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

CHARACTERISTICS

- Excellent workability.
- Great application with both hands.
- Thixotropic and anti-droop.
- Easy mixing.
- Fast absorption allowing immediate reworking.
- Damp-proofed product with fibres.
- Can be applied with or without reinforcements.
- High resistance to cracking.
- Weatherproof.
- Water vapour permeable.
- Excellent mechanical resistance.
- Excellent durability even in aggressive environments.
- Storage: 12 months in its original packaging and protected from moisture.

IDEAL FOR

- Floor repair.
- Fixing peeling walls.
- Cement rendering.
- Building brick partitions, etc.



Pallet of 35 boxes
of 4 x 5 Kg



Pallet of 42 boxes
of 12 x 1 Kg



Mixing water ratio

0,30 litres of water per kg of plaster



Performance

1.70 - 1.80 Kg/m²/mm



12.5 - 13.5



Maximum application thickness

Minimum: 1 mm
Maximum: 100 mm (filling and repairs)



Adherence

> 11 Kg/cm² on cement



Fire classification

A2 - s1 - d0



Use time

2 H - 2 H 45'



Drying time

Concrete: 3 - 4 H



Maximum granulometry

600 microns



BAIXENS ESPAÑA
POL. IND. MONCARRA, S/N
46230 ALGINET (VALENCIA)
T.: 961.750.834
F.: 961.752.471

BAIXENS FRANCE
14, RUE DU PONT NEUF
75001 PARIS (FRANCE)
T.: 0.800.90.14.37
F.: 0.800.90.20.52

BAIXENS ITALIA / BULOVA
VIA PIETRO NENNI, 36
46019 CICOGNARA - MANTOVA (ITALY)
T.: 0375/88181/790016 F.: 0375/88831
www.bulova-pennelli.com

BAIXENS PORTUGAL / ARGATINTAS
AVENIDA PORTAS DO MINHO, Nº 711
4760 - 706 RIBEIRÃO,
V.N. FAMALICÃO
T.: 252 910 030 | www.argatintas.pt

baixens.com
TESTING THE DIFFERENCE

B39NF1270A20