

RG-116

ISOLXTREM® SYSTEM

ISOLXTREM MESH

Fibreglass mesh indicated for reinforcing mortar in external thermal insulation composite systems (ETICS)



OUTDOOR



Width	100 cm \pm 1%
Length	50 m \pm 2%
Weight	160 g/m ²
Mesh light	3.5 x 3.8 mm
Thickness	\pm 0.52 mm
Fabric	Half-leno
Linear density	Warp: 25 x 2 tex Weft: 20.5 tex
Resistance to tension	Warp: \geq 2,200 N/ 5 cm Weft: \geq 2,200 N/ 5 cm
Resistance to tension <small>after 28 days in a sodium hydroxide 5% solution</small>	Warp: \geq 1,400 N/ 5 cm Weft: \geq 1,400 N/ 5 cm
Elongation	Warp: 3,8% Weft: 3.8%
Elongation <small>after 28 days in a sodium hydroxide 5% solution</small>	Warp: 3,5% Weft: 3.5%
ETAG 004 certification	



Pallet of 33
50 m² units.