


RX-112

Rualaix®

STANDARD

Plaster suitable for recoating and smoothing walls with small flaws. Medium setting



* representative information on the emissions of volatile substances in indoor air that present a toxicological risk by inhalation on a scale from C (high emissions) to A + (very low emissions).







COATE

BY ALL KINDS OF CONVENTIONAL NON- RESILIENT PAINTS AFTER COMPLETE DRYING

CLASSIFICATION ACCORDING TO UNE 48313: 2008 EX

G3S2V3W2A0C0R0

USE

Gypsum, plaster, cement and non-elastic synthetic paint. Substrates must be healthy, dry, cohesive, absorbent, well adhered, clean and free of dust.

FEATURES

- · Slow setting.
- Easy to apply, smooth and sand.
- Non-repellent.
- Applicable in thin layers.
- Storage: 12 months inside its original packing and kept free from damp and humidity.

IDEAL FOR

- · Recoating small fissures or micro-fissures.
- Recoating non-movement and non-structural feature cracks.
- Smoothing and plastering large surfaces.





Pallet of 66 sacks x 15 Kgs.



Pallet of 35 cases of 4 x 5 Kgs



Pallet of 36 cases of 20 x 1 Kg.



PREPARATION

0.43 - 0.48 litres of water per Kg. of plaster



PERFORMACE

1.58 – 1.64 Kg/m2/mm



6.0-7.0



MAXIMUM THICKNESS PER COAT 1 mm



ADHESION

>0,7 MPa on cement and paint



FIRE RESISTENCE CLASSIFICATION A1



USEFUL LIFE 8 Hrs. approx.



DRYNG TIMEConcrete and paint: 4 – 6 Hrs.
Plaster: > 7 Hrs.



MAXIMUM GRADING 300 microns