

# RX-116

**Rualaix®**

## BLUE LABEL

Plaster for filling and recoating cavities and cracks.



INTERIOR



### SURFACES

Gypsum, plaster, cement, concrete, brick, non-elastic synthetic paint, laminated gypsum panels and traditional masonry foundations.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

### CHARACTERISTICS

- Quick setting.
- Normal drying.
- No shrinkage.
- No cracking.
- Contains anti-cracking additives.
- May be applied in thin and thick layers.
- Easy to sand.
- Easy to apply.

### IDEAL FOR

- Filling fissures, cracks and holes.
- Recoating panel joints.
- Gluing mouldings.
- Recoating non-structural holes and cracks.

### ON-SITE APPLICATION

#### SURFACE PREPARATION

The surface must be sound, clean and free of any trace of saltpetre, fungi, microorganisms, grease, release oils and, in general, any type of material that could make it difficult for the product to adhere to the surface.




#### COVERING

FOR ALL TYPES OF CONVENTIONAL PAINT  
AFTER COMPLETE DRYING

CLASSIFICATION ACCORDING  
TO STANDARD EN 16566

**G3S2V3W2A0C0R0**



# RX-116

**Rualaix®**

## BLUE LABEL

### ON-SITE APPLICATION

#### CLEANING

If surfaces present traces of fungi, algae or other type of microorganisms, we first proceed to curative treatment with our **RX-526 CLEAN ENERGY**. Apply the product to the surface to be treated. After 5-10 minutes of action, clean the surface using a pressurised water machine or with a hard bristle brush.

Then, once the surface is completely dry, **RX-524 CLEAN MICRO** should be applied until the surface is completely impregnated. This preventive treatment is very effective and prevents future presence of microorganisms. If there are saltpetre stains on the surface to be treated, carry out an initial cleaning process with our **RX-523 CLEAN SAL**, applying the material and then scraping it with a hard bristle brush. After mechanically cleaning the surface, it will need to be rinsed with plenty of clean water in order to neutralise any **CLEAN SAL** residue that may remain on the surface.

Any grease or oil must be completely eliminated to allow the product to adhere correctly to the surface. Therefore, we recommend using **RX-527 CLEAN OIL** for correct and total elimination of these substances.

Powdery surfaces must be consolidated with a fixative (**FIJAPREN** line), since dust prevents adhesion between materials. Similarly, old surfaces made up of perished plaster or poorly adhered parts must be cleaned up: **restoring perished surfaces without prior restoration is totally inadvisable**. If there are holes in the surface, these should be scraped down and removed until a consistent surface is created, then a fixative (**FIJAPREN** line) should be applied to remove traces of dust. This consistent surface will usually be made of brick, cement, functional plaster or any other material, as long as it can support the weight and tension of the layers subsequently applied, without breaking up or having its structure altered.

If cracks are present these must be repaired, i.e. opened up and their interiors fixed using a fixative (**FIJAPREN** line), left to dry for at least 4 hours and then filled to the required level.

#### DIRECTIONS FOR USE

Knead with clean water at a ratio of 45% - 50% (450 ml - 500 ml water for each kg of plaster). Mixing should be carried out manually or mechanically using an electric mixer. Leave the paste to stand for a few minutes and then apply.

For cavity filling, we recommend using a medium sized spatula that allows for good pressure inside the cavity. Where possible, ensure that the width of the spatula is slightly greater than the size of the cavity.

When the material is dry, sand it and, if there are no imperfections, apply a fixative and then paint.

# RX-116

**Rualaix®**

## BLUE LABEL

### TECHNICAL CHARACTERISTICS

Useful life	30' - 60'
Shore hardness	81
Maximum granulometry	200 µm
pH	6.0 - 7.0
Maximum thickness	8 mm for plastering Unlimited for filling
Tool cleaning	with water
Fire classification	A1

Drying time in 1 mm layer on plaster surface (*)	3 - 4 H
Drying time in 1 mm layer on concrete and paint surface (*)	4 - 5 H

(\*) Depends on the environmental conditions, the nature of the surface and the thickness of application.

#### PERFORMANCE

kilograms of powder applied per m <sup>2</sup> in 1 mm thickness	0,90 - 1,05
--	-------------

#### DENSITY

DUST (g/ml)	PASTE (g/ml)
0.73 ± 0.07	1.52 ± 0.07

#### ADHERENCES

TEST	RESULT
Initial adhesion on cement	> 6 kg/cm <sup>2</sup>
Initial adhesion on paint	> 6 kg/cm <sup>2</sup>

### INFORMATION OF INTEREST

The Rualaix range manufacturing process is controlled in batches, which allows traceability of any incident. The quality system used includes each article's design and production controls, both in terms of the raw materials used, guaranteeing uniform manufacturing, and the final item obtained. The use of ecotechnologies in our facilities' manufacturing processes allows for efficient work, without damaging the environment that surrounds us.

- Non-flammable product.
- Avoid bringing the product into contact with skin and eyes.
- Smoking, eating and drinking must be prohibited in the application area.
- Comply with workplace health and safety legislation.
- Keep the product in a dry place, in original containers that are kept properly closed.
- Store the containers between 5°C and 35°C.
- Recommended storage time: 12 months from the date of manufacture, in its original packaging and protected from moisture.

For further information on protective measures and first aid, please refer to the product's Safety Data Sheet.

RX-116

Rualaix®

BLUE LABEL

## COMMENTS

- For appropriate use and correct application of the product, it is essential to first read the technical data sheet.
- The data provided in this data sheet are for guidance only and should not be considered binding. The data has been obtained in normal laboratory conditions and on standardised surfaces, and can vary depending on the conditions in which they are applied (absorption of the surface, applied thickness, temperature, environmental humidity, etc.). The intervals displayed have been shaped by measurement history. Slight deviations from the ranges presented in this technical sheet, whether higher or lower, will be accepted according to internal technical criteria and will not result in a loss of quality or affect the performance of the final product, due, among other factors, to variations in measurement conditions and the uncertainty associated with the instruments used.
- The working conditions of the users are out of our control.
- The product must not be used for purposes other than those specified We recommend strictly following the recommendations for use.
- Do not exceed the maximum recommended application thickness.
- It is essential that the status of the surfaces be assessed prior to each application.
- Use the product within its useful lifetime Beyond this time, unfavourable properties may arise.
- Do not apply on damp or warm surfaces.
- Do not apply on non-absorbent or extremely crystalline surfaces.
- Do not mix with any material, as the product will not retain its technical characteristics.
- Application temperature: from 5°C to 35°C.
- Maximum relative humidity: 85%.
- Do not re-knead when the product has started to set.
- The technical department of **ESTABLECIMIENTOS BAIXENS** states that the designs of recently launched new products are considered to be in an experimental phase until an annual history can be constituted. From then on, the newly designed product is considered to be fully consolidated in the market. In the meantime, **BAIXENS** reserves the right to adapt its variable specifications or working ranges according to technical criteria. The data subject to modification will be identified with an asterisk for easy identification and may be recently created products and / or experimental phase products or improvements in our various ranges due to market needs and / or requirements.
- We place at your disposal a technical-commercial team that will advise you regarding any doubt or query.

## PACKAGING

FORMAT	15 Kg	5 Kg	1 Kg
UNIT/BOX	–	4	20
PALLETS	66 SACS	35 BOXES	36 BOXES



Internal code	RX116NF1519A20
---------------	----------------



*Testing the difference*

**BAIXENS ESPAÑA**  
POL. IND. MONCARRA, S/N  
46230 ALGINET (VALENCIA)  
T.: 961.750.834  
F.: 961.752.471

**BAIXENS FRANCE**  
14, RUE DU PONT NEUF  
75001 PARIS (FRANCE)  
T.: 0.800.90.14.37  
F.: 0.800.90.20.52

**BAIXENS ITALY / BULOVA**  
VIA PIETRO NENNI, 36  
46019 CICOGNARA - MANTOVA (ITALY)  
T.: 0375/88181790016 F.: 0375/88831  
www.bulova-pennelli.com

**BAIXENS PORTUGAL / ARGATINTAS**  
AVENIDA PORTAS DO MINHO, Nº 711  
4760 - 706 RIBEIRÃO,  
V.N. FAMILIÇÃO  
T.: 252 910 030  
www.argatintas.pt