

RX-401


Rualaix®

PASTA EXTERIORES

Brilliant white plaster suitable for smoothing and re-coating of walls and façades..
Fibrous



* information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions).



INFORMATION ON DIRECTIVE 2004/42/CE
CATEGORY I1, HIGH PERFORMANCE ONE COMPONENT COATINGS, WATER-BASED

Limit: 140 g/l COV (2007); 140 g/l COV (2010)
This product contains 13,11 g/l COV max.

RECOATING

BY ALL TYPES OF NON-ELASTIC PAINTS, ONCE COMPLETELY DRY

CLASSIFICATION ACCORDING TO REGULATION

NF T36-005: FAMILY III - CLASS 2

CODE (EN 16-565)

G3S2V2W2A0C0R0

USE

Gypsum, plaster, cement, non-elastic synthetic paint, traditional varnishes, tiles.
Substrates must be healthy, dry, cohesive, absorbent, well adhered, clean and free of dust.

FEATURES

- Brilliant white.
- Fibrous.
- Easy to apply and excellent workability.
- Extraordinary finesse.
- Easy to apply, smooth and sand.
- Powerful grip.
- Thin layer applicable.
- Storage: 12 months inside its original packing and kept free from damp and humidity.

IDEAL FOR

- Plastering walls and façades, independent of their grade of absorption.



15Kg Pallet of 33 buckets of 15 kg.

5Kg Pallet of 24 cases of 4 x 5 kg.

1Kg Pallet of 44 cases of 12 x 1 kg.



Preparation

Ready to use.
Clean tools with water.



Performance

1.70 - 1.80 Kg/m²/mm



Maximum thickness per coat

1 mm



Adhesion

> 12 Kg/cm² on paint
> 18 Kg/cm² on concrete



8.0 - 9.0



Fire resistance classification

A2 - s1 - d0



Useful life

Unlimited



Drying time in 1 mm thickness

Plaster and paint: 1 - 3 hrs.
Concrete: 1 Hr. approx.



Maximum granulometry/grading

200 microns with no fibre thread