

RX-413

Rualaix®

FILLER

Ready-to-use fibre-reinforced plaster suitable for filling in imperfections and levelling out irregularities.



INFORMATION ON DIRECTIVE 2004/42/EC

CATEGORY i1, HIGH PERFORMANCE COMPONENT COATINGS, WATERBASED

Limit: 140 g/l VOC (2007); 140 g/l VOC (2010)

This product contains max. < 140 g/l VOC

COVERING

FOR ALL TYPES OF CONVENTIONAL PAINT
AFTER COMPLETE DRYING

CLASSIFICATION ACCORDING
TO STANDARD EN 16566

G3S2V2W3A2C0R0

SURFACES

Gypsum, plaster, laminated gypsum panels, cement, laminated cement boards, concrete, wood, polystyrene, furniture, doors, non-elastic synthetic paint and absorbent supports in general.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

CHARACTERISTICS

- Excellent workability.
- Easy to smooth and sand.
- Minimal shrinkage.
- Non-repellent.
- Excellent filling capacity.
- Great adhesion, cohesion and hardness.
- Reinforced with fibreglass.
- It can be tinted.

IDEAL FOR

- Filling gaps and cracks.
- Smoothing, repairing and sealing wood surfaces.
- Levelling out irregular substrates.
- Repairing gypsum and polystyrene decorative elements.

ON-SITE APPLICATION

SURFACE PREPARATION

The surface must be sound, clean and free of any trace of saltpetre, fungi, microorganisms, grease, release oils and, in general, any type of material that could make it difficult for the product to adhere to the surface.



* Information représentative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle allant de C (fortes émissions) à A+ (très faibles émissions)

RX-413

Rualaix®

FILLER

ON-SITE APPLICATION

CLEANING

When the supports present traces of fungi, algae or other types of microorganisms, we will proceed with the curative treatment, first of all, with a quick mold cleaner. This will be applied to the surface to be treated and after 5 -10 minutes of action, the support will be cleaned with the help of a pressurized water machine or with a hard bristle brush. Next, and once the support is completely dry, a broad-spectrum biocide cleaner will be applied until the support is completely impregnated. This treatment is called preventive, it is very effective and serves to prevent the future appearance of microorganisms. If there are saltpetre stains on the surface to be treated, carry out an initial cleaning process with our **RX-523 CLEAN SAL**, applying the material and then scraping it with a hard bristle brush. After mechanically cleaning the surface, it will need to be rinsed with plenty of clean water in order to neutralise any **CLEAN SAL** residue that may remain on the surface.

Any grease or oil must be completely eliminated to allow the product to adhere correctly to the surface. Therefore, we recommend using **RX-527 CLEAN OIL** for correct and total elimination of these substances.

Powdery surfaces must be consolidated with a fixative (**FIJAPREN** line), since dust prevents adhesion between materials. Similarly, old surfaces made up of perished plaster or poorly adhered parts must be cleaned up: **restoring perished surfaces without prior restoration is totally inadvisable**. If there are holes in the surface, these should be scraped down and removed until a consistent surface is created, then a fixative (**FIJAPREN** line) should be applied to remove traces of dust. This consistent surface will usually be made of brick, cement, functional plaster or any other material, as long as it can support the weight and tension of the layers subsequently applied, without breaking up or having its structure altered.

If cracks are present these must be repaired, i.e. opened up and their interiors fixed using a fixative (**FIJAPREN** line), left to dry for at least 4 hours and then filled to the required level.

DIRECTIONS FOR USE

Ready-to-use material. Do not dilute.

Smoothing should always be carried out vertically from the bottom to the top of the surface with a wide or smooth trowel (preferably with a rounded edge), applying the material and then removing the excess, taking care to smooth and cover all surface defects. Joints are smoothed in reverse, from top to bottom. When the material is dry, sand it and then apply another coat of plaster horizontally from right to left, applying it on joints from left to right.

For cavity filling, we recommend using a medium sized spatula that allows for good pressure inside the cavity. Where possible, ensure that the width of the spatula is slightly greater than the size of the cavity.

Finally, when the material is dry, sand it and, if there are no imperfections, apply a fixative and then paint.

RX-413

Rualaix®

FILLER

TECHNICAL CHARACTERISTICS

Density	1.64 ± 0.07
Reaction to fire	A2 - s1 - d0
Maximum granulometry	200 µm
pH	7.0 - 8.0
Shore C hardness	81
Drying time in 1 mm layer on absorbent surfaces (*)	12 H
Maximum thickness per layer	15 mm
Tool cleaning	With water

Direct traction adhesion (EN 1542)	≥ 1.0 MPa
Capillary absorption and permeability to liquid water (EN 1062-3)	< 0.1 Kg/(m ² · h ^{0.5})
Water vapor permeability (EN ISO 7783)	Clase 1
Hazardous substances:	Complies with section 5.3 of EN 15651- 1
Crack resistance at 23°C (EN 1062-7)	Clase A2

(*) Depends on the environmental conditions, the nature of the surface and the thickness of application.

PERFORMANCE	
kilograms of paste applied per m ² in 1 mm thickness	145 - 1.65

ADHERENCES	
CEMENT	PAINT
> 9 kg/cm ²	> 10 kg/cm ²

INFORMATION ON DIRECTIVE 2004/42/EC - Category i1	
VOC LIMIT	VOC CONTENT
140 g/l (2007) - 140 g/l (2010)	< 140 g/l max.

INFORMATION OF INTEREST

The Rualaix range manufacturing process is controlled in batches, which allows traceability of any incident. The quality system used includes each article's design and production controls, both in terms of the raw materials used, guaranteeing uniform manufacturing, and the final item obtained. The use of ecotechnologies in our facilities' manufacturing processes allows for efficient work, without damaging the environment that surrounds us.

- Non-flammable product.
- Avoid the product coming into contact with skin and eyes.
- Smoking, eating and drinking must be prohibited in the application area.
- Comply with legislation on health and safety at work.
- Keep the product in a dry place, in original containers that are kept properly closed.
- Store the containers between 5°C and 35°C.
- Recommended storage time: 12 months from the date of manufacture in its original packaging and protected from moisture.

For further information on protective measures and first aid, please refer to the product's Safety Data Sheet.

RX-413

Rualaix®

FILLER

COMMENTS

- For appropriate use and correct application of the product, it is essential to first read the technical data sheet.
- The data provided in this data sheet are for guidance only and should not be considered binding. The data has been obtained in normal laboratory conditions and on standardised surfaces, and can vary depending on the conditions in which they are applied (absorption of the surface, applied thickness, temperature, environmental humidity, etc.). The intervals displayed have been shaped by measurement history. Slight deviations from the ranges presented in this technical sheet, whether higher or lower, will be accepted according to internal technical criteria and will not result in a loss of quality or affect the performance of the final product, due, among other factors, to variations in measurement conditions and the uncertainty associated with the instruments used.
- The working conditions of the users are beyond our control.
- The product must not be used for purposes other than those specified. It is recommended that the recommendations for use be strictly followed.
- Do not exceed the maximum recommended application thickness per coat.
- It is essential that the status of the surfaces be assessed prior to each application.
- Do not apply on non-absorbent surfaces.
- Do not mix with any material, as it will not retain its technical characteristics.
- We do not recommended applying the product on aged, badly adhered paints.
- Application temperature: from 5°C to 35°C.
- Maximum relative humidity: 85%.
- The technical department of **ESTABLECIMIENTOS BAIXENS** states that the designs of recently launched new products are considered to be in an experimental phase until an annual history can be constituted. From then on, the newly designed product is considered to be fully consolidated in the market. In the meantime, **BAIXENS** reserves the right to adapt its variable specifications or working ranges according to technical criteria. The data subject to modification will be identified with an asterisk for easy identification. These may be recently created products and/or products in an experimental phase or improvements in our various ranges due to market needs and/or demands.
- We place a technical-commercial team at your disposal that will advise you on any doubts or queries.

PACKAGING

FORMAT	5 kg	1 kg	310 ml
UNIT/BOX	4	12	12
PALLETS	24 BOXES	44 BOXES	120 BOXES



Internal code	RX413NF1756A20
---------------	----------------



BAIXENS

baixens.com

Testing the difference

BAIXENS ESPAÑA
POL. IND. MONCARRA, S/N
46230 ALGINET (VALENCIA)
T.: 961.750.834
F.: 961.752.471

BAIXENS FRANCE
14, RUE DU PONT NEUF
75001 PARIS (FRANCE)
T.: 0.800.90.14.37
F.: 0.800.90.20.52

BAIXENS ITALIA / BULOVA
VIA PIETRO NENNI, 36
46019 CICOGNARA - MANTOVA (ITALY)
T.: 0375/88181/790016 F.: 0375/88831
www.bulova-pennelli.com

BAIXENS PORTUGAL / ARGATINTAS
AVENIDA PORTAS DO MINHO, Nº 711
4760 - 706 RIBEIRÃO,
V.N. FAMALICÃO
T.: 252 910 030
www.argatintas.pt