

RX-806

Unijunta®

LIGHT PASTE

Suitable for filling joints between plasterboard sheets.
Reduced density.



UNE13963
3A

Q1-Q4

INTERIOR



USES

Plasterboard sheets.

Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

FEATURES

- Great finesse and quality finishes.
- Excellent workability.
- Easy to smooth and sand.
- Excellent adhesion.
- Great filling power.
- Lightened product.
- Storage: 12 months inside its original packing and kept free from damp and humidity.

IDEAL FOR

- Filling joints between plasterboard sheets merging paper or fibre tape.
- Repairing small flaws such as lines, dents and scratches on plasterboard sheets.
- Thin layer complete rendering of the plasterboard sheets (Q4 finish).



INFORMATION ON DIRECTIVE 2004/42/CE

CATEGORY i1, HIGH PERFORMANCE ONCE COMPONENT
WATER-BASED COATINGS

Limit: 140G/L COV (2007); 140g/l COV (2010)
This product contains: 0,11g/l COV max.

COATED

BY ALL TYPES OF CONVENTIONAL NON-RESILIENT PAINTS
AFTER COMPLETELY DRYING

CLASSIFICATION ACCORDING TO STANDARD
UNE-EN 13963

3A

QUALITY LEVEL 4 (Q4)



Pallet of 33
buckets of 15 l.



Pallet of 120
buckets of 4 l.



Preparation
Ready to use



Performance
0,115 - 0,195 l/m²/mm
± 0,150 l/m lineal



6.0 - 7.0



Maximum thickness for joining
10 mm



Adhesion
> 3 Kg/cm² on plaster
> 8 Kg/cm² on concrete



Fire Classification
A2 - s1 - d0



Useful life
Unlimited.



Drying Time in 1 mm thickness
3 - 4 H



Maximum Granulometry
50 Microns