

RX-808

Unijunta®

1 Hr. SETTING

Suitable for filling joints between plasterboard sheets.
Fast setting.

**COATED**

BY ALL TYPES OF CONVENTIONAL NON-RESILIENT PAINTS
AFTER COMPLETELY DRYING

CLASSIFICATION ACCORDING TO STANDARD
UNE-EN 13963

3 B STANDARD

QUALITY LEVEL 4 (Q4)

USES

Plasterboard sheets.
Surfaces must be sound, dry, cohesive, absorbent, well adhered, clean and free of dust.

FEATURES

- Great finesse and quality finishes.
- Excellent workability.
- Easy to smooth and sand.
- Excellent adhesion.
- Great filling power.
- Fast setting.
- Quick dry in thin layer.
- Storage: 6 months inside its original packing and kept free from damp and humidity.

IDEAL FOR

- Relleno de juntas entre placas de cartón yeso intercalando cinta de papel o fibra
- Reparación de pequeños defectos tales como rayas, golpes y arañazos sobre placas de cartón yeso
- Enlucido total de las placas de cartón yeso en capa fina (acabado Q4)



Palet de 66
sacos de 15 kg.



Palet de 35 cajas
de 4 x 5 kg.

**Water for mixing**

0,45 – 0,50 litres of water per kg of powder.

**Performance**

250 - 300 g/m²/mm



7.5 - 8.5

**Maximum thickness for joining**

10 mm

**Adhesion**

> 10 Kg/cm² on concrete

**Fire Classification**

A1

**Useful life**

1 Hr. approx.

**Drying Time in 1 mm thickness**

Plaster: 1 H 30' - 2 H

**Maximum Granulometry**

300 Microns